



BITUMEN MASTIC WEARING COURSE

BITUMEN MASTIC WEARING COURSE FOR ROAD SURFACE

PROVIDING & LAYING BITUMEN MASTIC
AS PER THE SPECIFICATIONS OF MOSRT & H.



SCHEDULE ITEM FOR BITUMEN MASTIC FLOORING

| Sr. No. | Description of item | Unit |
|----------------|---|------|
| D S R 16.37 | Providing and laying bitumen mastic wearing course (as per specifications) with industrial bitumen of grade 85/25 conforming to IS : 702 prepared by using mastic cooker and laid to required level and slope including providing antiskid surface with bitumen precoated fine grained hard stone chipping of approved size at the rate of 0.005 cum per 10 sqm and at approximates spacing of 10cm centre to centre in both direction, pressed into surface protruding 1mm to 4mm over mastic surface, including cleaning the surface, removal of debris etc. all complete. (Considering bitumen using 10.2% as per MORTH specification.) | sqm. |
| 16.37.1 | 25mm thick. | sqm. |
| 16.37.2 | 40mm thick. | sqm. |

